

View Online at <https://aerobasegroup.com/nsn/3040-01-284-5391>

End Application:

Bru-47/a bomb rack, 1095-01-251-7900, f-15 acft

Special Features:

Material copper beryllium casting per ams 4890 or copper beryllium bar per qq-c-530, condition at; heat treat to 165, 000 psi; rockwell hardness c36-41; chrome plate 0.0007-0.0010 in. Thk per qq-c-320, class 2d, type 2 except inner dia; outside diameter 0.750 in., inner diameter 0.5005-0.5015 in.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A50800