

View Online at <https://aerobasegroup.com/nsn/3110-00-689-9939>

General Description:

Steel, grade 4140 or 4150, astm a322, or astm a331, or steel, grade 4140 h, astm a519; heat treatment= heat at 1535-1565 deg. F., oil quench, temper, immediately for 1 hr. At heat to hardness specified; manganese phosphate, type m, per mil-p-16232, class 1; 5.868 in. Lg.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No