

View Online at <https://aerobasegroup.com/nsn/3110-01-176-6402>

**Cross Sectional Shape:**

Counterbored w/ aperture

**Outside Diameter:**

Between 3.360 inches and 3.380 inches

**Minor Thickness:**

0.0705 inches

**Mounting Hole Diameter:**

Between 0.296 inches and 0.303 inches

**Aperture Diameter:**

2.953 inches

**Overall Thickness:**

Between 0.711 inches and 0.735 inches

**End Application:**

Aircraft eng f-101

**Hardness Rating:**

Between 26.0 rockwell c and 32.0 rockwell c

**Counterbore Diameter:**

Between 2.680 inches and 2.720 inches

**Counterbore Depth:**

Between 0.640 inches and 0.665 inches

**Mounting Hole Type:**

Round, unthreaded

**Special Features:**

Four tabs 0.660 in. Min 0.700 in. Maximum located on 4.440 dbc; magnetic particle insp per ams-2640; personnel qualification per military standard 410 reqd; process shall be fluorescent and continuous w5 gauss maximum residual magnetism allowed

**Material:**

Steel comp 4340

**Surface Treatment:**

Oxide

**Surface Treatment Specification:**

Ams-2485 assn standard single treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A093a0