

View Online at <https://aerobasegroup.com/nsn/3120-01-176-1026>

**Overall Length:**

0.3850 inches

**Body Outside Diameter:**

0.4378 inches

**Body Inside Diameter:**

0.2509 inches

**Corner Shape:**

Square all corners

**Cubic Measure:**

0.07379 cubic inches

**Surface Finish:**

63.0 microinches outside diameter surface of body

**Special Features:**

Bore is countersunk on both ends to 62.0 deg. And 0.020 in. Deep; for 416 heat treat to rockwell c35-39 (160, 000-180, 000 psi tensile strength)per mil-h-6875; for 17-4ph heat treat to cond. H1025 (age harden at 1025 deg. For4 hrs.)per mil-h-6875, part to be free of heat treatment discoloration or oxidation scale; salt spray and humidity tests are waived for type iv passivation

**Material:**

Stainless steel

**Material Specification:**

Ams5643, type 17-4ph, sol tr assn standard single material response or astm a582, type 416, cond. A (cold finished) assn standard single material response

**Surface Treatment:**

Passivate

**Surface Treatment Specification:**

Qq-p-35, type i, ii, or iii, for17-4ph; type iv for 416 federal specification single treatment response

**Style Designator:**

17c solid, plain, no outside flanges

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A045a0