

View Online at <https://aerobasegroup.com/nsn/3120-01-338-1050>

**Bore Diameter:**

Between 0.3745 inches and 0.3750 inches

**Outer Member Outside Diameter:**

Between 0.8120 inches and 0.8125 inches

**Outer Member Width:**

Between 0.3070 inches and 0.3170 inches

**Inner Member Width:**

Between 0.4040 inches and 0.4060 inches

**Hardness Rating:**

43.0 rockwell c inner member and 47.0 rockwell c inner member 28.0 rockwell c outer race member and 37.0 rockwell c outer race member

**Material:**

Steel comp xm-13 inner member steel comp 630 outer race member plastic polytetrafluoroethylene race liner

**Material Specification:**

Ams 5629 assn standard single material response inner member ams 5643 assn standard single material response outer race member

**Surface Treatment:**

Passivate inner member

**Surface Treatment Specification:**

Qq-p-35 federal specification single treatment response inner member

**Style Designator:**

With insert and/or liner with staking groove

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A045a0