

View Online at <https://aerobasegroup.com/nsn/3120-01-352-8509>

**Bore Diameter:**

Between 0.1895 inches and 0.1900 inches

**Outer Member Outside Diameter:**

Between 0.5620 inches and 0.5625 inches

**Outer Member Width:**

Between 0.2130 inches and 0.2230 inches

**Inner Member Width:**

Between 0.2760 inches and 0.2810 inches

**Hardness Rating:**

55.0 rockwell c inner member and 62.0 rockwell c inner member 28.0 rockwell c outer race member and 40.0 rockwell c outer race member

**Material:**

Steel comp 440c inner member steel comp 630 outer race member

**Material Specification:**

Ams 5630 assn standard single material response inner member ams 5643 assn standard single material response outer race member

**Surface Treatment:**

Passivate inner member

**Surface Treatment Specification:**

Qq-p-35 federal specification single treatment response inner member

**Style Designator:**

Without insert or liner with staking groove

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A045a0