

View Online at <https://aerobasegroup.com/nsn/3120-01-352-8509>

Bore Diameter:

Between 0.1895 inches and 0.1900 inches

Outer Member Outside Diameter:

Between 0.5620 inches and 0.5625 inches

Outer Member Width:

Between 0.2130 inches and 0.2230 inches

Inner Member Width:

Between 0.2760 inches and 0.2810 inches

Hardness Rating:

55.0 rockwell c inner member and 62.0 rockwell c inner member 28.0 rockwell c outer race member and 40.0 rockwell c outer race member

Material:

Steel comp 440c inner member steel comp 630 outer race member

Material Specification:

Ams 5630 assn standard single material response inner member ams 5643 assn standard single material response outer race member

Surface Treatment:

Passivate inner member

Surface Treatment Specification:

Qq-p-35 federal specification single treatment response inner member

Style Designator:

Without insert or liner with staking groove

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A045a0