NSN 3439-01-477-5372

Metallic Overlay Welding Powder - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/3439-01-477-5372

| _ | | | | | |
|----|-----|----|-----|-----|----|
| ĸэ | sic | RЛ | 210 | ria | ١. |
| | | | | | |

Carbide, chromium and nickel

Content Within Each Unit Package:

12.5lbs

Special Features:

Nsn used to purchase a of 16containrs to a of 39containers; certification pwa 1305, ge b50tf137 class a, avco m3965 and rr 9507/17; rc 50-55 hardness; 3000 psi strength; best finish be wet sanding; mixture of 75% crystalline chromium carbide and 25% nickel chromium alloy powder.1000-1500 degrees (f) for resistance to abrasive and fretting type wears. Coatin gs are hard, dense and tightly adherent. Particulary suited for thin smooth coatings

| Sh | elf | Lif | e: |
|----|-----|-----|----|
| | | | |

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T166-s