## NSN 3439-01-477-7569

Fiig: T166-s

Metallic Overlay Welding Powder - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/3439-01-477-7569

3
Basic Material:
Magnesium
Content Within Each Unit Package:
12.5lbs
Special Features:
Nsn used to purchase a of 160 containers and up; certification pwa 1333, ge a50tf155 and rr 9507/21; rc 30-35 hardness; 1200 psi
strength; grind only, use silicon carbide or diamond wheels. Magnesium stabilized zirconium oxide powder, widely used in aircraft engine
industry for thermal barrier coatings. Outstanding resistance to thermal shock and particle erosion
Shelf Life:
N/a
Unit Of Measure:
<del></del>
Demilitarization:
No