## NSN 3439-01-477-8407

Metallic Overlay Welding Powder - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/3439-01-477-8407

Rasi	<u>ا ما</u>	٨л	2+	۸r	ial	١.

Nickel-chromium alloy

**Content Within Each Unit Package:** 

12.5lbs

## **Special Features:**

Nsn used to purchase a of 40containrs to a of 79containers; certification ams 4775 and aws bni-1; basic primary nickel-chromium-silicon-boron brazing filler material widely used for heat resistant, high strength joints. Used extensively in jet engine applications for joining turbine components, highly stressed sheet mtal parts and other highly stressed structures. Brazing range 1970-2200deg (f), solidus 1790deg (f) and liquidus 1970deg (f)

She	lf L	.ife:

N/a

**Unit Of Measure:** 

**Demilitarization:** 

No

Fiig:

T166-s