NSN 3439-01-478-4062

Metallic Overlay Welding Powder - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/3439-01-478-4062

Environmental Protection:
Any acceptable
Basic Material:
Cerium and zirconium silicate
Content Within Each Unit Package:
12.5lbs
Special Features:
Nsn is used to purchase a of 24 containers and up; zr o 25ce o 2.5y o; -90 +16 um (-170 mesh +16 um); rc 30-35 hardness; texture/finish
as-sprayed 350-500; cerium oxzide, yttrium oxide stablized zirconium oxide powder. Spherical free flowing and fully alloyed powder
particles.Produces the best thermal barrier coatings (tbc's) in terms of lowest thermal conductivity and resistance to fatigue caused by
thermal cycling. Coatings also exhibit resistance to high tempreature degradation caused by fuel contaminants in jet engines. Recommended
for protection of critical metal components from heat and particle erosion at elevated tempreatures. Ideally suited for severe thermal barrier
applications and offers greater high tempreature corrosion resistance against sodium, sulfur and chlorine contaminants compared to 8%
yttria zirconia coatings
Shelf Life:
N/a
Unit Of Measure:
-
Demilitarization:
No
Fiig:
T166-s