

View Online at <https://aerobasegroup.com/nsn/3439-01-509-3611>

**End Application:**

Navy equipment spares

**Physical Form:**

Wire

**Chemical Composition Percentage:**

Tine 62.5 to 63.5; lead remainder; antimony 0.20 to 0.50; bismuth maximum 0.25; copper maximum 0.08; iron maximum 0.02; zinc maximum 0.005; aluminum maximum 0.005; arsenic maximum 0.03; total other 0.08

**Wire Core Type:**

Rosin

**Special Features:**

Ansi/j-std-004-1995, -005-1995, -006-1995; tin-lead eutectic

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

T166-c