

View Online at <https://aerobasegroup.com/nsn/3439-01-657-4565>

Special Features:

Exothermic mixture that react to produce molten metal and a ceramic phase by-product.

Supplementary Features:

Reaction temperatures can exceed 4000 degrees (2200 degrees c) producing molten metal in exdcress of 2500 degrees f(1370 degrees c) .

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No