

View Online at <https://aerobasegroup.com/nsn/3680-01-290-0243>

General Description:

10 oz blocks supplied in 300 lb fibre drum; used at an application of 16 ozs per 100 lbs of metal, the block should be placed in the bottom of a hot crucible and the charge materials added on top of the blocks; recommended for red brass, tin bronze, leaded tin bronze

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A23900