

View Online at <https://aerobasegroup.com/nsn/4020-00-231-2541>

**Fabrication Method:**

Twisted

**Length:**

400.000 yards

**Environmental Protection:**

Mildew resistant

**Impregnation Material:**

Copper-8-quinolinolate

**Breaking Strength:**

2720.0 pounds

**Material And Location:**

Hemp, manila or fiber, sisal or fiber, jute or fiber, cotton

**Issue Form:**

Coil

**Length Per Weight:**

14.700 feet per pound

**Length Per Ten Turns:**

Between 16.125 inches and 17.750 inches

**Circumference:**

1.500 inches

**Strand Quantity:**

3

**Breaking Strength:**

2720.0 pounds

**Color:**

Natural

**Material And Location:**

Jute or sisal or cotton or manila

**Specification Or Standard:**

1 type and 2 class

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A15300