

View Online at <https://aerobasegroup.com/nsn/4020-00-298-3394>

Fabrication Method:

Twisted

Length:

15.000 feet

Environmental Protection:

Mildew resistant

Impregnation Material:

Copper-8-quinolinolate

Rope Style:

Loop and plain end

Breaking Strength:

2650.0 pounds

Rope End Conditioning Method:

Served

Length Per Weight:

13.300 feet per pound

Length Per Ten Turns:

16.125 inches

Loop Retention Method:

Splice

Inner Perimeter:

8.000 inches

Assembly Material And Location:

Hemp, manila, t-r-605, type m, class 2 rope

Circumference:

1.500 inches

Strand Quantity:

3

Color:

Natural

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A15300