Fibrous Rope - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/4020-00-641-2342



Fabrication Method:

Twisted

Length:

200.000 yards

Impregnation Material:

Oil preservative

Breaking Strength:

18500.0 pounds

Material And Location:

Hemp, manila, t-r-605, type m, class 1

Issue Form:

Coil

Length Per Weight:

1.670 feet per pound

Length Per Ten Turns:

42.312 inches

Circumference:

4.500 inches

Strand Quantity:

3

Breaking Strength:

18500.0 pounds

Color:

Natural

Material And Location:

Manila

Material Specification:

T-r-605, type m, class 1 federal specification single material response

Specification Or Standard:

M type and 1 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A15300