

View Online at <https://aerobasegroup.com/nsn/4710-00-277-4044>

Pipe Size Designation:

2.500 inches

Wall Thickness Designation:

Schedule 40

First End Style:

Plain

Welding Method:

Furnace butt

Second End Relationship With First End:

Identical

Construction:

Straight seamed

Measuring Method And Length:

144.000 inches random and 288.000 inches random

Special Features:

0.203 in. Wall thk; 2.875 in. Od

Heat Treatment:

Quenched and tempered

Material:

Steel comp 304

Material Specification:

66 federal standard single material response or aisi 304 assn standard single material response or sae 30304 assn standard single material response

Specification Or Standard:

2 type and 3 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A004a0

Mil-std (military Standard):

Mil-p-1144 spec.