

View Online at <https://aerobasegroup.com/nsn/4710-00-288-7927>

Cross Sectional Shape:

Plain round

Wall Thickness:

0.156 inches

First End Style:

Plain

Welding Method:

Furnace butt

Diameter:

2.000 inches

Second End Relationship With First End:

Identical

Construction:

Seamless

Measuring Method And Length:

144.000 inches random and 288.000 inches random

Heat Treatment:

Annealed

Material:

Steel

Surface Treatment:

Zinc

Surface Treatment Specification:

Qq-z-351-cancelled federal specification single treatment response

Specification Or Standard:

1 type

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A004a0

Mil-std (military Standard):

Mil-t-16343 spec.