

View Online at <https://aerobasegroup.com/nsn/4710-00-541-3234>

Cross Sectional Shape:

Plain round

Wall Thickness:

0.065 inches

First End Style:

Plain

Welding Method:

Furnace butt

Diameter:

0.500 inches

Second End Relationship With First End:

Identical

Construction:

Seamless

Measuring Method And Length:

120.000 inches random and 144.000 inches random

Heat Treatment:

Cold drawn 1/4 hard condition

Material:

Steel comp 304

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A004a0