

View Online at <https://aerobasegroup.com/nsn/4710-00-554-8926>

Cross Sectional Shape:

Plain round

Wall Thickness:

0.035 inches

First End Style:

Plain

Welding Method:

Double submerged arc

Diameter:

0.625 inches

Second End Relationship With First End:

Identical

Construction:

Straight seamed

Measuring Method And Length:

120.000 inches random and 288.000 inches random

Heat Treatment:

Annealed

Material:

Steel comp 1010 or steel comp 1015

Surface Treatment:

Phosphate

Specification Or Standard:

3 type

Departure From Cited Document:

As modified by surface treatment

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A004a0