

View Online at <https://aerobasegroup.com/nsn/4720-01-496-5729>

Cross Sectional Shape:

Wall Thickness:

0.125 inches

Inside Diameter:

0.250 inches

Nonmetallic Hardness Rating:

80.0 shore durometer a and 90.0 shore durometer a

Temperature Rating:

175.0 degrees fahrenheit single response

Outside Diameter:

0.500 inches

Exterior Color:

Clear

End Application:

Aircraft, stratolifter c-135

Min. Tensile Strength (psi):

5500 pounds per square inch

Burst Test Pressure:

524.0 pounds per square inch single response

Maximum Operating Pressure:

131.0 pounds per square inch single response

Inside Surface Condition:

Smooth

Special Features:

Superthane ether; resistant to weathering, tearing, impact, radiation and abrasion; approved by seg for transfer of contaminated clean liquids

Material:

Plastic polyurethane tube

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A54200