

View Online at <https://aerobasegroup.com/nsn/4920-01-059-6469>

End Application:

An/asq-153 field age., test pattern projector set

General Description:

Matl.-optical glass per mil-g-174, class 1, type 517-642, gr b; 5.000 in. Dia.; thickness varies with spherical radius; inner and outer centers of curvature to be concentric to within 0.001 in.; inner and outer surfaces shall be anti-reflection coated with magnesium flouride per mil-c-675, coating optimized for 1.06 microns

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli