

View Online at <https://aerobasegroup.com/nsn/4920-01-070-5734>

**End Application:**

F100 pw100 engine age.

**Special Features:**

Matl: aluminum 6061; weld in 0 or t4 condition harden to t6 brinell hardness 90 min. After welding

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A505c0