

View Online at <https://aerobasegroup.com/nsn/5220-01-467-7670>

Special Features:

Test area 0.375 in. Dia; measures 0.8 to 2.0 mils (20 to 50 microns); accuracy and reproducibility of 0.3 military (8 microns) or better at profile of 1 mil; complies with astm d-4417

Functional Description:

Used to provide a permanent profile record of grit or shot blasted surface

General Description:

Layer of 2.6 mils (65 microns) thickness of crushable plastic microfoam coated onto polyester film 2.0 mils (50 microns) of highly uniform thickness

Type/model Designation:

Testex press-o-film replica tape, 0.8-2mils coarse

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No