

View Online at <https://aerobasegroup.com/nsn/5220-01-467-9310>

Special Features:

9test area 0.375 in. Dia; measures 1.5 to 4.5 mils (35 to 115 microns); accuracy and reproducibility of 0.8 military (18 microns) at profile of 2.0 mils (50 microns) and 1.5 mils (37 microns) at profile of 4.0 mils (100 microns); complies with astm d-4417

Functional Description:

Used to provide a permanent profile record of grit or shot blasted surface

General Description:

Layer of 2.6 mils (65 microns) thickness of crushable plastic microfoam coated onto polyester film 2.0 mils (50 microns) of highly uniform thickness

Type/model Designation:

Testex press-o-film replica tape, 1.5-4.5 mils x-coarse

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No