

View Online at <https://aerobasegroup.com/nsn/5310-00-274-8715>

**Hole Diameter:**

Between 0.255 inches and 0.263 inches

**Outside Diameter:**

0.489 inches

**Material Thickness:**

0.062 inches

**End Application:**

W/s: stream (std. Tensioned replenishment at sea method); aircraft, c-2a (repreocured); vehicle, aircraft refueler r-14; test consoles, mini-sace; support equipment, b-1 aircraft; teletype, model 28; helicopter, mh-53e; machine gun, .50 cal, m2, hb, flex & hvytt fixed; aircraft (ac-130h, mc-130h, ec-130e, hc-130); mrap rg-33 and rg-33 auv

**Hardness Rating:**

Between 45.0 rockwell c and 53.0 rockwell c

**Material:**

Steel comp 1060 or steel comp 1561 or steel comp 1064 or steel comp 1065 or steel comp 1566 or steel comp 1069 or steel comp 1070 or steel comp 1572 or steel comp 1074 or steel comp 1075 or steel comp 1080

**Surface Treatment:**

Phosphate

**Surface Treatment Specification:**

Mil-p-16232 type 2 military specification single treatment response

**Style Designator:**

Split helical-right hand

**Specification Or Standard:**

A class and 2 style

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fig:**

A022b0

**Mil-std (military Standard):**

Mil-p-16232 spec.