

View Online at <https://aerobasegroup.com/nsn/5310-01-063-3792>

Hole Diameter:

Between 1.755 inches and 1.765 inches

Outside Diameter:

2.625 inches

External Prebent Key Length:

0.251 inches

External Prebent Key Width:

Between 0.247 inches and 0.250 inches

Material Thickness:

Between 0.423 inches and 0.438 inches

Hardness Rating:

Between 25.0 rockwell c and 32.0 rockwell c

External Prebent Key Angle:

30.0 degrees

Special Features:

Two external keys prebent inward instead of outward and chamfer 0.060 in. By 45 degrees one edge

Heat Treatment:

Quenched and tempered

Material:

Steel comp 4130 or steel comp 5130 or steel comp 8630

Surface Treatment:

Phosphate

Surface Treatment Specification:

Mil-p-16232, ty m, cl 2 military specification single treatment response

Style Designator:

Key

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A022b0

Mil-std (military Standard):

Mil-p-16232 spec.