NSN 5310-01-331-6778

Flat Washer - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5310-01-331-6778

Rectangular Hole Diameter: Between 0.990 inches and 1.101 inches Edge Shape: Round Center Hole Shape: 1 round Thickness: 0.030 inches Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Alterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Sheft Life: N/a Unit Of Measure: — Demilitarization: No Fitig: A02250 Mil-s-5059 spec.	Cross Sectional Shape:
Between 0.990 inches and 1.101 inches Edge Shape: Round Conter Hole Shape: 1 round Thickness: 0.030 inches Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qcp-35 federal specification: Qcp-36 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Flig: A022b0 Mil-std (military Standard):	Rectangular
Edge Shape: Round Center Hole Shape: 1 round Thickness: 0.030 inches Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mill-s-5059, type 301 military specification 1st material response or mill-s-5059, type 302 military specification 2nd material response or mill-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Filig: A02250 Mill-std (military Standard):	Hole Diameter:
Round Center Hole Shape: 1 round Thickness: 0.030 inches Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Between 0.990 inches and 1.101 inches
Center Hole Shape: 1 round Thickness: 0.030 inches Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Sleel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Edge Shape:
1 round Thickness: 0.030 inches Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mill-s-5059, type 301 military specification 1st material response or mill-s-5059, type 302 military specification 2nd material response or mill-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Filg: A022b0 Mill-std (military Standard):	Round
Thickness: 0.030 inches Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A02250 Mil-std (military Standard):	Center Hole Shape:
Ouerall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	1 round
Overall Diameter: Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Thickness:
Between 1.190 inches and 1.210 inches End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A02250 Mil-std (military Standard):	0.030 inches
End Application: Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Overall Diameter:
Afterbody section, torpedo mk50 Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Between 1.190 inches and 1.210 inches
Material: Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	End Application:
Steel comp 301 or steel comp 302 or steel comp 304 Material Specification: Mil-s-5059, type301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Afterbody section, torpedo mk50
Material Specification: Mil-s-5059, type301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Material:
Mil-s-5059, type 301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-s-td (military Standard):	Steel comp 301 or steel comp 302 or steel comp 304
mil-s-5059, type 304 military specification 3rd material response Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Material Specification:
Surface Treatment: Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Mil-s-5059, type301 military specification 1st material response or mil-s-5059, type 302 military specification 2nd material response or
Passivate Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	mil-s-5059, type 304 military specification 3rd material response
Surface Treatment Specification: Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Surface Treatment:
Qq-p-35 federal specification single treatment response Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Passivate
Shelf Life: N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Surface Treatment Specification:
N/a Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Qq-p-35 federal specification single treatment response
Unit Of Measure: Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	Shelf Life:
Demilitarization: No Fiig: A022b0 Mil-std (military Standard):	N/a
No Fiig: A022b0 Mil-std (military Standard):	Unit Of Measure:
No Fiig: A022b0 Mil-std (military Standard):	
Fiig: A022b0 Mil-std (military Standard):	Demilitarization:
A022b0 Mil-std (military Standard):	No
Mil-std (military Standard):	Fiig:
	A022b0
Mil-s-5059 spec.	Mil-std (military Standard):
	Mil-s-5059 spec.