

View Online at <https://aerobasegroup.com/nsn/5315-00-005-0558>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

Between 0.865 inches and 0.885 inches

Pindiameter:

Between 0.1571 inches and 0.1573 inches

First End Taper Length:

Between 0.016 inches and 0.047 inches

Second End Taper Length:

0.036 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Not identical

Hardness Rating:

58.0 rockwell c and 64.0 rockwell c

Shear Strength:

4100 double pounds per square inch

First End Taper Angle:

Between 20.0 degrees and 30.0 degrees

Surface Finish:

16.0 microinches outside diameter

Second End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Special Features:

Small chamfer end may have 0.016 in. Min 0.047 in. Maximum radius in lieu of chamfer

Material:

Steel

Material Specification:

Fed standard 66 federal standard single material response

Surface Treatment:

Cadmium

Surface Treatment Specification:

Qq-p-416, type 2, cl 3 federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0