

View Online at <https://aerobasegroup.com/nsn/5315-00-026-3198>

First End Style:

Chamfered

Pinlength:

Between 0.427 inches and 0.447 inches

Pindiameter:

Between 0.1876 inches and 0.1878 inches

First End Taper Length:

0.016 inches

Second End Relationship With First End:

Identical

Hardness Rating:

40.0 rockwell c and 45.0 rockwell c

Shear Strength:

105000 single pounds per square inch

First End Taper Angle:

45.0 degrees

Material:

Steel comp 630

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-s-5002 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-s-5002 spec.