

View Online at <https://aerobasegroup.com/nsn/5315-00-026-6621>

First End Style:

Chamfered

Overall Length:

Between 0.990 inches and 1.010 inches

Diameter:

Between 0.3740 inches and 0.3745 inches

Effective Length:

Between 0.750 inches and 0.755 inches

Undercut Diameter:

Between 0.350 inches and 0.354 inches

Undercut Width:

Between 0.028 inches and 0.030 inches

Second Undercut Width:

Between 0.028 inches and 0.030 inches

First End Taper Length:

Between 0.005 inches and 0.025 inches

Second End Relationship With First End:

Identical

Hardness Rating:

55.0 rockwell c and 60.0 rockwell c

First End Location:

Both ends

First End Taper Angle:

Between 40.0 degrees and 50.0 degrees

Surface Finish:

32.0 microinches outside diameter

Material:

Steel comp 1020

Material Specification:

Sae assn standard single material response

Surface Treatment:

Phosphate zinc or phosphate manganese

Surface Treatment Specification:

Mil-c-16232 type 2 military specification 1st treatment response or mil-c-16232 type 1 military specification 2nd treatment response

Style Designator:

Groove

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-c-16232 spec.