

View Online at <https://aerobasegroup.com/nsn/5315-00-057-3539>

**First End Style:**

Chamfered

**Inside Diameter:**

0.250 inches

**Pinlength:**

3.530 inches

**Pindiameter:**

Between 1.4960 inches and 1.4980 inches

**First End Taper Length:**

0.020 inches

**Second End Relationship With First End:**

Identical

**Hardness Rating:**

43.0 rockwell c and 46.0 rockwell c

**First End Taper Angle:**

Between 43.0 degrees and 47.0 degrees

**Special Features:**

Both ends counterbored 1.120 in. Diameter by 0.600 in. Deep, counterbored ends countersunk 60.0 degrees by 0.104 in. Deep /optional/

**Material:**

Steel comp 4340 and steel

**Material Specification:**

Aisi assn standard 1st material response and cva1-585, cond c-1 fscm 16615 mfr ref 2nd material response

**Surface Treatment:**

Chromium

**Test Data Document:**

81349-mil-i-6868 specification (includes engineering type bulletins, brochures, etc., that reflect specification type data in specification format; excludes commercial catalogs, industry directories, and similar trade publications, reflecting general type data on certain environmental and performance requirements and test conditions that are shown as "typical", "average", "", etc.).

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A212a0