

View Online at <https://aerobasegroup.com/nsn/5315-00-059-5845>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

Between 1.990 inches and 2.010 inches

Pindiameter:

Between 0.6251 inches and 0.6253 inches

First End Taper Length:

0.357 inches

Second End Taper Length:

Between 0.062 inches and 0.125 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Not identical

Hardness Rating:

47.0 rockwell c and 58.0 rockwell c

Shear Strength:

78000 double pound

First End Taper Angle:

Between 4.0 degrees and 16.0 degrees

Second End Taper Angle:

Between 20.0 degrees and 30.0 degrees

Special Features:

Small chamfer end may have 0.062 in. Min 0.125 in. Maximum radius in lieu of chamfer

Material:

Steel

Material Specification:

Astm a29 assn standard single material response

Surface Treatment:

Phosphate zinc

Surface Treatment Specification:

Dod-p-16233 ty z cl 2 national specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0