

View Online at <https://aerobasegroup.com/nsn/5315-00-089-4943>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

Between 0.865 inches and 0.885 inches

Pindiameter:

Between 0.1571 inches and 0.1573 inches

First End Taper Length:

Between 0.016 inches and 0.047 inches

Second End Taper Length:

0.036 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

First End Taper Angle:

Between 20.0 degrees and 30.0 degrees

Surface Finish:

16.0 microinches outside diameter

Second End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Special Features:

Small chamfered end may have 0.016 in. Min 0.047 in. Maximum radius in lieu of chamfer

Material:

Steel comp 410 or steel comp 416

Material Specification:

66 federal standard all material responses

Surface Treatment:

Passivate

Surface Treatment Specification:

Qq-p-35 type 2 or 3 federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0