

View Online at <https://aerobasegroup.com/nsn/5315-00-112-2246>

First End Style:

Chamfered

Pinlength:

Between 0.390 inches and 0.400 inches

Pindiameter:

Between 0.1567 inches and 0.1572 inches

First End Taper Length:

Between 0.010 inches and 0.025 inches

Second End Relationship With First End:

Identical

Hardness Rating:

26.0 rockwell c and 32.0 rockwell c

First End Taper Angle:

Between 44.0 degrees and 46.0 degrees

Surface Finish:

40.0 microinches

Material:

Steel comp 8630 or steel comp 4130

Material Specification:

Mil-s-6050 military specification 1st material response and mil-s-6758 military specification 2nd material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-s-6050 spec.