

View Online at <https://aerobasegroup.com/nsn/5315-00-133-3602>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

Between 1.240 inches and 1.260 inches

Pindiameter:

Between 0.2509 inches and 0.2511 inches

First End Taper Length:

Between 0.031 inches and 0.062 inches

Second End Taper Length:

0.053 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

Shear Strength:

7200 double pounds per square inch

First End Taper Angle:

Between 20.0 degrees and 30.0 degrees

Surface Finish:

16.0 microinches outside diameter

Second End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Special Features:

Small chamfer end may have 0.031 in. Min 0.062 in. Maximum radius

Material:

Steel comp 410 or steel comp 416

Material Specification:

66 federal standard all material responses

Surface Treatment:

Passivate

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0