

View Online at <https://aerobasegroup.com/nsn/5315-00-143-6485>

First End Style:

Chamfered

Second End Style:

Radius

Pinlength:

Between 0.615 inches and 0.635 inches

Pindiameter:

Between 0.1571 inches and 0.1573 inches

Second End Corner Radius:

0.052 inches

First End Taper Length:

0.120 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 42.0 rockwell c

Shear Strength:

2800 double pound

First End Taper Angle:

Between 4.0 degrees and 16.0 degrees

Surface Finish:

16.0 microinches outside diameter

Special Features:

Radius end may be chamfered 25.0 deg

Material:

Steel comp 410 or steel comp 416

Material Specification:

Fed standard 66 federal standard all material responses

Surface Treatment:

Passivate

Surface Treatment Specification:

Qq-p-35, type 2 federal specification single treatment response or qq-p-35, type 3 federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0