

View Online at <https://aerobasegroup.com/nsn/5315-00-149-8615>

**First End Style:**

Chamfered

**Pinlength:**

Between 3.488 inches and 3.512 inches

**Pindiameter:**

Between 0.2495 inches and 0.2505 inches

**First End Taper Length:**

Between 0.010 inches and 0.030 inches

**Features Provided:**

Casehardened

**Second End Relationship With First End:**

Identical

**Hardness Rating:**

58.0 rockwell c and 64.0 rockwell c

**First End Taper Angle:**

Between 20.0 degrees and 30.0 degrees

**Special Features:**

Core hardness rockwell c scale 40 min, 64 max

**Material:**

Steel comp 1090 or steel comp 1095

**Material Specification:**

Astm a576 assn standard all material responses

**Surface Treatment:**

Cadmium and chromate or cadmium and phosphate

**Surface Treatment Specification:**

Qq-p-416, type 2 cl 2 federal specification 1st treatment response or qq-p-416, type 3 cl 2 federal specification 2nd treatment response

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A212a0