

View Online at <https://aerobasegroup.com/nsn/5315-00-149-8615>

First End Style:

Chamfered

Pinlength:

Between 3.488 inches and 3.512 inches

Pindiameter:

Between 0.2495 inches and 0.2505 inches

First End Taper Length:

Between 0.010 inches and 0.030 inches

Features Provided:

Casehardened

Second End Relationship With First End:

Identical

Hardness Rating:

58.0 rockwell c and 64.0 rockwell c

First End Taper Angle:

Between 20.0 degrees and 30.0 degrees

Special Features:

Core hardness rockwell c scale 40 min, 64 max

Material:

Steel comp 1090 or steel comp 1095

Material Specification:

Astm a576 assn standard all material responses

Surface Treatment:

Cadmium and chromate or cadmium and phosphate

Surface Treatment Specification:

Qq-p-416, type 2 cl 2 federal specification 1st treatment response or qq-p-416, type 3 cl 2 federal specification 2nd treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0