

View Online at <https://aerobasegroup.com/nsn/5315-00-162-3002>

First End Style:

Radius

Pinlength:

Between 0.215 inches and 0.225 inches

Pindiameter:

Between 0.0590 inches and 0.0610 inches

First End Corner Radius:

Between 0.003 inches and 0.014 inches

Second End Relationship With First End:

Identical

Hardness Rating:

55.0 rockwell c and 60.0 rockwell c

Surface Finish:

63.0 microinches outside diameter

Material:

Steel comp 440c

Material Specification:

Ams 5630 assn standard single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Sp-151 fscm 66503 mfr ref single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0