

View Online at <https://aerobasegroup.com/nsn/5315-00-164-5651>

First End Style:

Chamfered

Pinlength:

Between 0.620 inches and 0.630 inches

Pindiameter:

Between 0.1240 inches and 0.1243 inches

First End Taper Length:

0.015 inches

Second End Relationship With First End:

Identical

Hardness Rating:

35.0 rockwell c and 40.0 rockwell c

First End Taper Angle:

45.0 degrees

Material:

Steel comp 410

Material Specification:

Ams 5613 assn standard single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Sp-151 fscm 66503 mfr ref single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0