

View Online at <https://aerobasegroup.com/nsn/5315-00-168-6207>

First End Style:

Chamfered

Pinlength:

0.970 inches

Pindiameter:

Between 0.4365 inches and 0.4370 inches

First End Taper Length:

Between 0.020 inches and 0.030 inches

Second End Relationship With First End:

Identical

Hardness Rating:

55.0 rockwell c and 60.0 rockwell c

First End Taper Angle:

30.0 degrees

Criticality Code Justification:

Achu

Surface Finish:

16.0 microinches outside diameter

Material:

Steel comp 440c

Material Specification:

Qq-s-763 federal specification single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Cps6515 fscm 71791 mfr ref single treatment response

Test Data Document:

81349-m-i-6868 specification (includes engineering type bulletins, brochures, etc., that reflect specification type data in specification format; excludes commercial catalogs, industry directories, and similar trade publications, reflecting general type data on certain environmental and performance requirements and test conditions that are shown as "typical", "average", "", etc.).

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0