

View Online at <https://aerobasegroup.com/nsn/5315-00-240-6175>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

Between 0.110 inches and 0.130 inches

Pindiameter:

Between 0.0626 inches and 0.0628 inches

First End Taper Length:

Between 0.008 inches and 0.016 inches

Second End Taper Length:

0.036 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 42.0 rockwell c

First End Taper Angle:

Between 30.0 degrees and 40.0 degrees

Surface Finish:

16.0 microinches outside diameter

Second End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Special Features:

Small chamfer end may have 0.008 in. Min 0.015 in. Maximum radius in lieu of chamfer

Material:

Steel comp 410 or steel comp 416

Surface Treatment:

Passivate

Surface Treatment Specification:

Qq-p-35 federal specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0