

View Online at <https://aerobasegroup.com/nsn/5315-00-275-8239>

First End Style:

Chamfered

Overall Length:

Between 1.080 inches and 1.100 inches

Effective Length:

Between 0.820 inches and 0.825 inches

Undercut Diameter:

Between 0.281 inches and 0.286 inches

Undercut Width:

Between 0.070 inches and 0.076 inches

Second Undercut Width:

Between 0.3740 inches and 0.3745 inches

First End Taper Length:

0.031 inches

Second End Relationship With First End:

Identical

Hardness Rating:

40.0 rockwell c and 45.0 rockwell c

First End Location:

Both ends

First End Taper Angle:

45.0 degrees

Surface Finish:

16.0 microinches outside diameter

Material:

Steel comp 1137

Surface Treatment:

Phosphate

Surface Treatment Specification:

Mil-p-16232, ty m, cl 1 military specification single treatment response

Style Designator:

Groove

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-p-16232 spec.