

View Online at <https://aerobasegroup.com/nsn/5315-00-276-3980>

First End Style:

Chamfered

Overall Length:

Between 0.983 inches and 1.003 inches

Diameter:

Between 0.341 inches and 0.342 inches

Effective Length:

Between 0.750 inches and 0.760 inches

Undercut Diameter:

Between 0.319 inches and 0.323 inches

Undercut Width:

Between 0.028 inches and 0.031 inches

First End Taper Length:

0.031 inches

Second End Relationship With First End:

Identical

Hardness Rating:

40.0 rockwell c and 45.0 rockwell c

First End Location:

Both ends

First End Taper Angle:

45.0 degrees

Surface Finish:

32.0 microinches outside diameter

Material:

Steel comp 1137 or steel comp 1139 or steel comp 1140 or steel comp 1141

Material Specification:

Aisi assn standard all material responses

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-s-5002 military specification single treatment response

Style Designator:

Groove

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-s-5002 spec.