

View Online at <https://aerobasegroup.com/nsn/5315-00-330-0623>

First End Style:

Chamfered

Pinlength:

0.625 inches

Pindiameter:

Between 0.3759 inches and 0.3761 inches

First End Taper Length:

0.015 inches

Second End Relationship With First End:

Identical

Hardness Rating:

30.0 rockwell c and 35.0 rockwell c

First End Taper Angle:

Between 40.0 degrees and 50.0 degrees

Surface Finish:

32.0 microinches outside diameter

Material:

Steel comp 4130

Surface Treatment:

Phosphate manganese

Surface Treatment Specification:

Mil-c-16232, tym, cl 1 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-c-16232 spec.