

View Online at <https://aerobasegroup.com/nsn/5315-00-404-3052>

First End Style:

Chamfered

Pinlength:

Between 2.490 inches and 2.510 inches

Pindiameter:

Between 0.2495 inches and 0.2497 inches

First End Taper Length:

Between 0.030 inches and 0.050 inches

Hardness Rating:

40.0 rockwell c and 47.0 rockwell c

Criticality Code Justification:

Achu

Surface Finish:

32.0 microinches outside diameter

Material:

Steel comp 630

Material Specification:

Ams 5643 assn standard single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-f-14072, e300 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A212a0

Mil-std (military Standard):

Mil-f-14072 spec.