

View Online at <https://aerobasegroup.com/nsn/5315-00-432-5414>

First End Style:

Chamfered

Second End Style:

Chamfered

Pinlength:

0.840 inches

Pindiameter:

Between 0.1259 inches and 0.1261 inches

First End Taper Length:

Between 0.010 inches and 0.050 inches

Second End Taper Length:

0.090 inches

Second End Relationship With First End:

Not identical

Hardness Rating:

36.0 rockwell c and 40.0 rockwell c

First End Taper Angle:

Between 20.0 degrees and 30.0 degrees

Surface Finish:

16.0 microinches outside diameter

Second End Taper Angle:

Between 4.0 degrees and 12.0 degrees

Special Features:

First end has one flat 0.140 in. Lg, 0.051 in. Dp

Material:

Steel comp 416

Material Specification:

Qq-s-763 federal specification single material response

Surface Treatment:

Passivate

Surface Treatment Specification:

Mil-f-14072, e300 military specification single treatment response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-f-14072 spec.