

View Online at <https://aerobasegroup.com/nsn/5315-00-435-0430>

First End Style:

Chamfered

Pinlength:

Between 0.440 inches and 0.460 inches

Pindiameter:

Between 0.1874 inches and 0.1876 inches

First End Taper Length:

Between 0.010 inches and 0.015 inches

Second End Relationship With First End:

Identical

Hardness Rating:

60.0 rockwell c and 62.0 rockwell c

First End Taper Angle:

Between 40.0 degrees and 50.0 degrees

Surface Finish:

16.0 microinches outside diameter

Material:

Steel comp 8740 or steel comp 4037

Material Specification:

Mil-s-6049 military specification 1st material response or ams 6300 assn standard 2nd material response

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A212a0

Mil-std (military Standard):

Mil-s-6049 spec.